

NEMA MW 750

**DYNAMIC COEFFICIENT
OF FRICTION OF
FILM-INSULATED
MAGNET WIRE**

NEMA Standards Publication No. MW 750-2009

Dynamic Coefficient of Friction of Film-Insulated Magnet Wire

Published by

National Electrical Manufacturers Association

1300 North 17th Street, Suite 1752
Rosslyn, VA 22209

www.nema.org

© Copyright 2009 by the National Electrical Manufacturers Association. All rights including translation into other languages, reserved under the Universal Copyright Convention, the Berne Convention for the Protection of Literary and Artistic Works, and the International and Pan American Copyright Conventions.

NOTICE AND DISCLAIMER

The information in this publication was considered technically sound by the consensus of persons engaged in the development and approval of the document at the time it was developed. Consensus does not necessarily mean that there is unanimous agreement among every person participating in the development of this document.

The National Electrical Manufacturers Association (NEMA) standards and guideline publications, of which the document contained herein is one, are developed through a voluntary consensus standards development process. This process brings together volunteers and/or seeks out the views of persons who have an interest in the topic covered by this publication. While NEMA administers the process and establishes rules to promote fairness in the development of consensus, it does not write the document and it does not independently test, evaluate, or verify the accuracy or completeness of any information or the soundness of any judgments contained in its standards and guideline publications.

NEMA disclaims liability for any personal injury, property, or other damages of any nature whatsoever, whether special, indirect, consequential, or compensatory, directly or indirectly resulting from the publication, use of, application, or reliance on this document. NEMA disclaims and makes no guaranty or warranty, expressed or implied, as to the accuracy or completeness of any information published herein, and disclaims and makes no warranty that the information in this document will fulfill any of your particular purposes or needs. NEMA does not undertake to guarantee the performance of any individual manufacturer or seller's products or services by virtue of this standard or guide.

In publishing and making this document available, NEMA is not undertaking to render professional or other services for or on behalf of any person or entity, nor is NEMA undertaking to perform any duty owed by any person or entity to someone else. Anyone using this document should rely on his or her own independent judgment or, as appropriate, seek the advice of a competent professional in determining the exercise of reasonable care in any given circumstances. Information and other standards on the topic covered by this publication may be available from other sources, which the user may wish to consult for additional views or information not covered by this publication.

NEMA has no power, nor does it undertake to police or enforce compliance with the contents of this document. NEMA does not certify, test, or inspect products, designs, or installations for safety or health purposes. Any certification or other statement of compliance with any health or safety-related information in this document shall not be attributable to NEMA and is solely the responsibility of the certifier or maker of the statement.

CONTENTS

	Page
Foreword	ii
Introduction	iii
History	iii
Section 1 GENERAL.....	1
1.1 Scope	1
1.2 Definition of Friction	1
1.3 Equipment Description	1
1.4 Discussion.....	1
1.5 References.....	2
Section 2 DYNAMIC COEFFICIENT OF FRICTION TEST METHOD.....	3
2.1 Definitions of Terms	3
2.2 Summary of method.....	3
2.3 Significance.....	3
2.4 Safety Statements.....	3
2.5 Apparatus.....	3
2.6 Test Specimen	6
2.7 Procedure.....	6
2.8 Calculation	7
2.9 Report	8
Tables	
2-1 Load Block Weights for Dynamic Coefficient of Friction Testing.....	7
Figures	
2-1 Diagram of a Typical Dynamic Coefficient of Friction Tester.....	4
2-2 Material—Sapphire (Synthetic).....	5
Photos	
2-1 Synthetic Sapphires Mounted on Load Block.....	5
2-2 Load Applied Perpendicular to Wire Path.....	7

FOREWORD

MW 750-2009 was prepared by the NEMA Magnet Wire Technical Committee.

NEMA Magnet Wire publications are periodically reviewed by the NEMA Magnet Wire Section for revisions considered necessary to keep them current with technology changes. Proposed revisions should be submitted to:

Vice President, Technical Services
National Electrical Manufacturers Association
1300 North 17th Street, Suite 1752
Rosslyn, VA 22209

This Standards Publication was approved by the NEMA Magnet Wire Section. Approval of a standard does not necessarily imply that all Section members voted affirmatively or participated in its development. At the time of approval, the Magnet Wire Section was composed of the following members:

CONDUMEX—Mexico City, Mexico
Bridgeport Insulated Wire Company—Bridgeport, CT
Elektrisola, Inc.—Boscawen, NH
Essex Group, Inc.—Fort Wayne, IN
Magnekon—San Nicolas de los Garza, NL, Mexico
MWS Wire Industries—Westlake Village, CA
Rea Magnet Wire Company, Inc.—Fort Wayne, IN

This document was approved as Authorized Engineering Information on October 7, 2009.

INTRODUCTION

As magnet wire is transferred from its packaging to coils, the designed path takes the wire over, around, and through guides, blocks, corners, and so forth, all of which are intended to help place the wire at the designed location in the coil.

The force required to pull the wire through the designed winding path, exclusive of the bending force, is that which is necessary to overcome the friction developed between the magnet wire and the various surfaces that come in contact with the wire. This force is directly related to the surface characteristics of the film insulation, the contact surfaces, and the applied lubrication.

HISTORY

Various devices have been used to measure the coefficient of friction of magnet wire. Several were discussed in Paper #4 at the NEMA session of the 1971 Electrical/Electronics Insulation Conference.

In 1961, Parussel described a tester to measure the coefficient of friction of film-insulated magnet wire. The design was subsequently standardized and incorporated in German Standards Institute (DIN) specifications. A tester similar to the Parussel design made by Excel Industries was later demonstrated to the NEMA Magnet Wire Technical Committee. At that time, an interest was expressed in redesigning the tester to simplify the operation.

In 1973, NEMA Engineering Bulletin No. 4 was developed by the NEMA Magnet Wire Section to describe the subject of coefficient of friction testing and provide a test method, including the final equipment description. Eventually, the original supplier of this equipment discontinued its interest in supplying equipment, and the Research Department at the Indiana Institute of Technology supplied a new design. In 1978, this test method was introduced for discussion at a meeting of International Electrotechnical Commission (IEC) Technical Committee 55, *Winding Wires*.

One of the critical elements of the test procedure was the selection of the surface that would be in contact with the wire specimen. Supplying and maintaining a prescribed steel surface ground to the applicable specifications was found to be cost prohibitive. As a proposed solution, representatives from The Netherlands recommended the use of synthetic sapphire elements for the load block surface. Their experience indicated that these synthetic sapphires would provide excellent life at low cost. The elements were subsequently adopted for the test surface.

Earlier versions of this equipment used a dynamometer to measure the tangential force (F_d). Since the value on the dynamometer continually varies, it was necessary for the operator to estimate the average force that occurs during the test. More precision and accuracy are required so that the gage repeatability and reproducibility can be improved for this test. The dynamometer has been replaced with a force transducer selected for this work, which is a linear variable differential transformer (LVDT). The data is collected from the pressure transducer readout by a computer or microprocessor. Statistical analysis can be performed on this data set resulting in mean, min, max, and standard deviation.

< This page is intentionally left blank. >

SECTION 1 GENERAL

1.1 SCOPE

This document describes a method and the equipment used for determining the dynamic coefficient of friction of film-insulated round magnet wire of sizes 14-44 AWG.